


DURA♦SKRIM® 8BV & 12BV

MEETS GRI-GM22 STANDARD SPECIFICATION



PRODUCT DESCRIPTION

DURA♦SKRIM® 8BV and 12BV consist of two sheets of high-strength virgin polyethylene film laminated together with a third layer of molten polyethylene. The black outer layers contain carbon black to enhance outdoor life. A heavy scrim reinforcement placed between these plies greatly enhances tear resistance and increases service life. DURA♦SKRIM®'s heavy-duty diamond reinforcement responds to tears immediately by surrounding and stopping the tear.



PRODUCT USE

DURA♦SKRIM® 8BV and 12BV are used in more demanding applications requiring high tear resistance. They are designed to withstand longer term outdoor applications requiring up to 5 years of exposure or more depending upon geographical location.

DURA♦SKRIM® 8BV and 12BV are designed to meet the requirements of the Geosynthetics Research Institute; GRI-GM22 Standard Specification.

SIZE & PACKAGING

DURA♦SKRIM® 8BV and 12BV are available in a variety of widths and panels up to 100,000 square feet. All panels are accordion folded and tightly rolled on a heavy-duty core for ease of handling and time-saving installation.



Temporary Rain Shed Cover

PRODUCT

PART

DURA♦SKRIM R8BV

DURA♦SKRIM R12BV

APPLICATIONS

- | | |
|---------------------------|------------------------------|
| Daily Landfill Covers | Remediation Covers or Liners |
| Interim Landfill Covers | Cargo Coverings |
| Temporary Rainshed Covers | Outdoor Covers |

DURA♦SKRIM® 8BV & 12BV

MEETS GRI-GM22 STANDARD SPECIFICATION

PROPERTIES	TEST METHOD	DURA♦SKRIM 8BV		DURA♦SKRIM 12BV	
		IMPERIAL	METRIC	IMPERIAL	METRIC
VV		Black/Black		Black/Black	
THICKNESS, NOMINAL		8 mil	0.20 mm	12 mil	0.30 mm
WEIGHT		38 lbs/MSF ₂ 5.5 oz./yd ²	185 g/m ²	58 lbs/MSF ₂ 8.4 oz./yd ²	283 g/m ²
CONSTRUCTION		Extrusion laminated with scrim reinforcement			
**1" TENSILE STRENGTH	ASTM D7003	70 lbf/in	122 N/cm	75 lbf/in	131 N/cm
**ELONGATION AT FILM BREAK	ASTM D7003	550 %	550 %	600 %	600 %
**ELONGATION AT SCRIM BREAK	ASTM D7003	16 %	16 %	18 %	18 %
**GRAB TENSILE	ASTM D7004	80 lbf	356 N	100 lbf	445 N
***TONGUE TEAR	ASTM D5884	30 lbf	133 N	40 lbf	178 N
CBR PUNCTURE RESISTANCE	ASTM D6241	200 lbf	890 N	270 lbf	1201 N
MULLEN BURST	ASTM D751	75 psi	517 kPa	100 psi	689 kPa
UV RESISTANCE (10,000 HR)	ASTM D882 GRI-GM16	>90% retained / no cracking		>90% retained / no cracking	
HIGH PRESSURE OIT		>1000 min.		>1000 min.	
MAXIMUM STATIC USE TEMPERATURE		180° F	82° C	180° F	82° C
MINIMUM STATIC USE TEMPERATURE		-70° F	-57° C	-70° F	-57° C
WVTR	ASTM E96 Procedure B	0.016 grains/(ft ² -hr)	0.274 g/(m ² -day)	0.010 grains/(ft ² -hr)	0.161 g/(m ² -day)
PERM	ASTM E96 Procedure B	0.039 Perms grains/(ft ² -hr-in Hg)	0.026 Perms g/(24hr-m ² -mm Hg)	0.023 Perms grains/(ft ² -hr-in Hg)	0.015 Perms g/(24hr-m ² -mm Hg)

**Tests are an average of primary reinforcement directions.

***Tests are an average of machine and transverse directions.

Hydraulic conductivity values are derived from permeability data. R8BV = 3.14 x 10⁻¹⁰ cm/sec, and R12BV = 1.85 x 10⁻¹⁰ cm/sec.

DURA♦SKRIM® 8BV and 12BV are both four-layer reinforced extrusion laminates. The outer layers consist of a high-strength polyethylene film containing carbon black and UV and thermal stabilizers.

DURA♦SKRIM® 8BV and 12BV are reinforced with a minimum of a 1000 denier scrim laid in a diagonal pattern spaced 3/8" apart with an additional machine direction scrim every 3" across the width.

DURA♦SKRIM®

Note: To the best of our knowledge, unless otherwise stated, these are typical property values and are intended as guides only, not as specification limits. Chemical resistance, odor transmission, longevity as well as other performance criteria is not implied or given and actual testing must be performed for applicability in specific applications and/or conditions. RAVEN INDUSTRIES MAKES NO WARRANTIES AS TO THE FITNESS FOR A SPECIFIC USE OR MERCHANTABILITY OF PRODUCTS REFERRED TO, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability for resulting loss or damage. Limited Warranty available at www.ravenefd.com

WIND DEFENDER®
4 South 2nd Street, Suite 206, Pottsville, PA 17901
Ph: +1 (570) 617-7479

© 2016 RAVEN INDUSTRIES INC. All rights reserved.

elliott@wind-defender.com
www.wind-defender.com

**WIND
DEFENDER®**

110416 EFD 1140WD