


Product Data Sheet



WIND DEFENDER® TG

Reversible reinforced geotextile windscreen made of knitted, tan and green, UV stabilized HDPE filament. Wind Defender is deployed and tensioned over an installed geomembrane in order to achieve a stable and reliable ballast system. Wind Defender can also standalone as a dust screen to prevent fugitive dust particles from leaving an area.

Nominal Product Values*			
Test	ASTM Method	English (Typical)	Metric (Typical)
Thickness	D 5199	55 mils	1.40mm
Mass/Unit Area	D 5261	6.50 oz/yd^2	220 g/m^2
Grab Strength	D 4632	MD 175 lbs	778 N
		XD-300 lbs	1,334 N
Grab Elongation	D 4632	MD-75%	MD-75%
		XD-60%	XD-60%
CBR Puncture	D 6241	700 lbs	3,113 N
UV Resistance at 15 months, 50C°, 20 hour UV, 4 hour condensation	D 7238	475 min HPOIT 65 lbs/in strength 65% elongation	475 min HPOIT 11.38 kN/m 65% elongation

Typical U.V. Resistance- 500 Hour Exposure				
Break Strength MD	D 4355	% retained	98	
Break Strength XD	D 4355	% retained	109	
Break Elongation MD	D 4355	% retained	101	
Break Elongation XD	D 4355	% retained	101	

Typical Roll Dimensions	English	Metric
Roll Length	328 ft	100 m
Roll Width	20 ft	6 m
Roll Area	6,560 sf	609 m^2
Roll Weight	305 lbs	138 kg

^{*}Nominal product values are average values with an acceptable maximum variance of - 10%

KEY BENEFITS

- · Aesthetically pleasing
- UV Stabilized
- Provides 60% UV block for underlying materials
- Installs quickly
- Available in large rolls
- · Performs well under snow load
- Lasts 3 to 10 times longer than most traditional sandbag and rope anchoring systems
- Safer to install than making and deploying heavy sandbags

APPLICATIONS

- Landfill Covers
- · Stockpile Covers
- Dust Screen
- · Soil Cover